FASHION STONE FASHION STONE GREY





Product code:	AGB09FNSEGRYZMLNLR		
Size:	30x60cm		
Series:	FASHION STONE		
Color:	GREY		
Typology:	PORCELAIN TILES		
Structure:	LIGHT STRUCTURE		
Surface look:	MATT		
Edge:	RECTIFIED		
Thickness:	8.5 mm		
Unity measure:	M²		

Dimensions: All dimensions in mm tolerance +5% for below 200mm and +3% for above 200mm. Thickness tolerance of $\pm5\%$ whichever is less.

Note: Due to a continuing development programme to improve design and performance, the manufacturer reserves all rights to vary specifications without prior information.

				RAK Ceramics Specifications	
	Test Description	Standard Test Method	International Standard ISO 13006	(Rectified)	(Unrectified)
$\stackrel{\textstyle \longleftrightarrow}{\longleftrightarrow}$	Length & Width	BS EN ISO 10545-2	+/- 0.6%	+/- 0.1%	+/- 0.3%
	Thickness	BS EN ISO 10545-2	+/-5.0%	+/- 5.0%	+/- 5.0%
	Rectangle Squareness	BS EN ISO 10545-2	+/- 0.5%	+/- 0.2%	+/- 0.4%
90°	Straightness of sides	BS EN ISO 10545-2	+/- 0.5%	+/- 0.2%	+/- 0.3%
	Surface Flatness	BS EN ISO 10545-2	+/- 0.5%	+/- 0.3%	+/- 0.3%
H ₂ 0)	Water Absorption	BS EN ISO 10545-3	<=0.5%	<=0.4%	<=0.4%
$\frac{\downarrow}{\uparrow\uparrow}$	Modulus of Rupture	BS EN ISO 10545-4	>=35 N/mm2	>=40 N/mm2	>=40 N/mm2
KG ↑ ↑	Breaking Strength	BS EN ISO 10545-4	>=1300N	>=1600N	>=1600N
0	Resistance to surface abrasion	BS EN ISO 10545-7	Manufacturer to state Abrasion Class	PEI Class 2 -5	PEI Class 2 -5
\searrow	Linear Thermal Expansion	BS EN ISO 10545-8	<=9x10 ⁶⁰ C1	<=7x10 ⁶ °C ¹	<=7x10 ⁻⁶⁰ C ⁻¹
+	Resistance to Thermal Shock	BS EN ISO 10545-9	No visible defect	No visible defect	No visible defect
举	Crazing Resistance	BS EN ISO 10545-11	No crazing	No crazing	No crazing
<u></u>	Frost Resistance	BS EN ISO 10545-12	No visible damage	No visible damage	No visible damage
	Resistance to chemicals	BS EN ISO 10545-13	No visible defect	No visible defect	No visible defect
*	Resistance to stains	BS EN ISO 10545-14	Manufacturer to state class	Stain removed Min.class 4	Stain removed Min.class 4
	Colour Resistance to UV Light	DIN 51094	No change in colour	No change in colour	No change in colour

Note: Shade variation across the batches is inherent to the manufacturing process and the pre-laying colour comparison is recommended